

# Effect of an electric field on nucleation and growth of crystals

V M Yurov<sup>1</sup>, S A Guchenko<sup>1</sup> and M S Gyngazova<sup>2</sup>

<sup>1</sup>E A Buketov Karaganda State University

<sup>2</sup>National Research Tomsk Polytechnic University, Tomsk, Russia

E-mail: exciton@list.ru

**Abstract.** The effect of the electric field strength on nucleation and growth of the crystals of ammonium halides and alkali metal sulfates has been studied. The optimal electric field strength for  $\text{NH}_4\text{Cl}$  and  $\text{NH}_4\text{Br}$  crystals was found to be 15 kV/cm, and for  $\text{NH}_4\text{I}$ , it equaled 10 kV/cm. No effect of the electric field strength on the crystal growth was found for alkali metal sulfates. This difference is analyzed in terms of the crystal growth thermodynamics. In case, when the electric field is small and the Gibbs energy is of a significant value, the influence of the electric field at the crystal growth is negligible. A method to estimate the critical radius of homogeneous nucleation of the crystal is suggested.

## 1. Introduction

The effect of electric, magnetic and other fields on nucleation and growth of various crystals has been studied since 50-ies of the last century. Some qualitative patterns were found and empirical models were suggested. However, the quantitative theory of these effects has not been worked out. This is primarily due to the lack of a rigorous theory of homogeneous nucleation. The main ideas of the theory of new phase nucleation were put forward by Gibbs and then developed by Volmer, Becker and Doring, Stransky and Kaishev, Frenkel and Zeldovich. According to this theory, the formation of small particles of a new phase in the metastable phase is considered as a fluctuation process. Despite this progress, there is no quantitative agreement between the theory and experimental data.

This is due to the fact that the size effects in the formation of crystal nuclei which have dimensions of the order of (1–5) nm are ignored. If we consider the size dependence of the surface tension at the interface only, classical theories of crystallization nucleation provide satisfactory quantitative agreement between theoretical and experimental data [1]. In [2], an additional force generated when applying the electric field was introduced. The results obtained in this research show that an electric field can either stimulate or inhibit the nucleation process depending on the ratio of the dielectric constant and orientation of the applied electric field relative to the surface nucleation. This approach is demonstrated in [3], which provides extensive bibliography on the effect of the electric field on crystal nucleation and growth. This issue is addressed in the reviews in [4–6].

## 2. Effect of the electric field on nucleation and growth of crystals of ammonium halides

A V Shubnikov [7] observed nucleation under the action of the electric field in the ammonium chloride solution. He attributed the observed phenomenon to the presence of the smallest dust particles in air which enter the solution and become the crystallization sites under the action of the electric field.



In [8], Kozłowski experimentally investigated the effect of the electric field on the solution of halides and sulfates. The field strength was varied from 1 to 30 kV/cm. The experiments showed that the electric field does not affect the sulphate solutions of nickel and copper and weakly impacts the nucleation process in the cadmium iodide solution. However, a significant impact of the field was observed on solutions of sodium and potassium chloride and  $\text{NH}_4\text{I}$ .

We have conducted a detail study of the effect of the electric field on nucleation and growth of ammonium halide crystals. Note that in [7, 8], as in many other studies, ammonium halides were produced in the form of dendrites. Nobody succeeded to produce single crystals of ammonium halides.

A small amount of urea was added to 90 % aqueous solution of , and . The temperature in the thermostat was maintained at 35 ° C. When the intensity of the electric field increased from 0 to 3 kV/cm, the number of centers increased as well. In the range from 3 to 15 kV/cm, the number of nuclei decreased, however, larger and more transparent crystals emerged. The optimal electric field strength for and was equal to 15kV/cm, and for it was 10 kV/cm.

### 3. Theoretical aspects of the effect of the electric field on crystal nucleation and growth

Thermodynamic methods used in [8] showed under the impact of the electric field, the crystallization pressure changes

$$P - P_0 = \frac{\beta E^2}{V_1 - V_2} \quad (1)$$

where  $\beta = \text{const}$ ,  $V_1$ ,  $V_2$  are the specific volumes of the first and second phases (per molecule), respectively.

The critical radius of the nucleus in the solid phase in the electric field:

$$r^* = \frac{2\sigma V_2}{\Delta\mu^0 - \beta E^2} \quad (2)$$

where  $\sigma$  is the coefficient of the surface tension at the solution-crystal interface;  $\Delta\mu^0$  is the chemical potential in the absence of the field.

For a one-component composition , where  $\Delta G$  is the Gibbs energy. According to [1] the N value is of the order of 100. Table 1 shows the values of the Gibbs energy (in modulus) for some of the substances taken from [9].

**Table 1.** Gibbs energy for some halides and sulfates [9]

Substance/Agent	$\Delta G$ (kJ/mol)	Substance/Agent	$\Delta G$ (kJ/mol)
KCl	408.490	CuSO <sub>4</sub>	661.070
NaCl	384.120	CuSO <sub>4</sub> ·5H <sub>2</sub> O	1377.780
NH <sub>4</sub> Cl	202.770	NiSO <sub>4</sub> ·6H <sub>2</sub> O	2680.050
AgCl	109.700	NiSO <sub>4</sub> ·7H <sub>2</sub> O	2459.640
AgBr	97.250	K <sub>2</sub> SO <sub>4</sub>	1318.790

Taking into account the remarks above equation (2) will take the form:

$$r_k = \frac{2\sigma v_2}{G/N - \beta E^2} \quad (3)$$

In case, when the electric field strength is low and the Gibbs energy is of a significant value, i.e.  $G/N \gg \beta E^2$ , the effect of the electric field on the crystal growth will be negligible. As can be seen in Table 1, the sulfate solution having a larger value of the Gibbs energy will be less affected by the electric field. This is consistent with the results reported in [2, 8].

#### 4. Evaluation of the critical radius of homogeneous nucleation of crystallization sites

The evaluation of the critical radius of homogeneous nucleation of pure metals can be carried out in the parameter  $d$ , which is determined by the size dependence of some physical property  $A(r)$  of metal (magnetic, electric, etc.) according to the formula [1]:

$$A(r) = A_0 \left( 1 - \frac{d}{r} \right), \quad (4)$$

where  $A_0$  is the physical property of the bulk sample.

Equation (4) is valid for both internal and external size effects. Therefore, the developed approach is valid not only for crystallization of pure metals, but for any other material. In this case, the parameter  $d$  can be determined by one of the proposed methods [10], and the formula  $r = r_c \geq d/3$  can be used to evaluate  $r_c$ .

We defined the parameter  $d$  of the intensity  $I(r)$  of the luminescence of crystalline powders of size. The parameter  $d = 2\sigma v / RT$ , where  $\sigma$  - the surface tension of the crystal,  $v$  - molar volume,  $R$  - the gas constant,  $T$  - temperature. The coordinates  $I(r) \sim 1/r$  a straight line is obtained according to formula (4). The slope of this straight line gives the value of  $d$ .

**Table 2.** Surface tension and critical radius of the alkali metal halides.

Chemical formula	Surface tension $\sigma$ (J / m <sup>2</sup> )	The critical radius $r_k$ (nm)
NaCl	0.158	1.095
NaBr	0.138	1.181
NaI	0.118	1.283
KCl	0.141	1.414
KBr	0.123	1.420
KI	0.113	1.597
RbCl	0.130	1.497
RbBr	0.114	1.502
RbI	0.104	1.654

Tables 2 and 3 show values of the surface tension and the critical radius halides and sulfates of alkali metals. From these tables it follows that the critical radius at sulfates of alkali metals slightly larger than alkali metal halides. However, the difference in the critical radius is not as great as one would expect. This means that the electric field does not act on the nucleation process, and on their growth in accordance with the formula (3).

**Table 3.** Surface tension and critical radius sulphates of alkali and alkaline earth metals.

Chemical formula	Surface tension $\sigma$ (J / m <sup>2</sup> )	The critical radius $r_k$ (nm)
Li <sub>2</sub> SO <sub>4</sub>	0.141	1.862
Na <sub>2</sub> SO <sub>4</sub>	0.124	1.753
K <sub>2</sub> SO <sub>4</sub>	0.117	2.044
Rb <sub>2</sub> SO <sub>4</sub>	0.112	2.209
Cs <sub>2</sub> SO <sub>4</sub>	0.110	2.504
BeSO <sub>4</sub>	0.240	2.690
MgSO <sub>4</sub>	0.166	2.003
CaSO <sub>4</sub>	0.189	2.958
SrSO <sub>4</sub>	0.180	2.226
BaSO <sub>4</sub>	0.175	2.421

### 5. A simple model

Here we want to show a simple model, which gives some idea of the physical process of homogeneous nucleation of a new phase. In a homogeneous medium with the particle number density  $n$  probability  $W(r)$  is the first that the nearest neighbor is at a distance  $r_k$  from the selected particles, is easily obtained from the classical statistical physics, and it is equal to:

$$W(r_k) = 4\pi n r_k^2 \exp\left[-4\pi n^2 r_k^3 / 3\right] \quad (5)$$

The probability of finding  $N$  particles in the embryo radius  $r_k$  is obviously  $W_N(r_k) = \prod_{i=1}^N W_i(r_k)$ .

The probability (5), we define the other hand, as the ratio of energy Bohr atom ( $E = z^2/2a$ ,  $z$  – charge,  $a = \text{const}$ ) to the total energy (ideal gas) ( $3/2nkT_0$ ). This is done, something to qualitatively assess whether the different critical radius  $r_k$  of the embryo, for example, for different metals. Thus, we have:

$$\frac{z^2/2a \cdot N}{3/2nkT_0} = (4\pi n)^N r_k^N \exp\left[-4\pi N n^2 r_k^3 / 3\right] \quad (6)$$

Taking the logarithm of both sides of (6), and performing simple transformations, we obtain:

$$-9 \ln 10 + \ln \left( \lambda \frac{Z^2}{T_0} \right) + \frac{3}{2} n \frac{T_0}{\Delta T} = \frac{4\pi}{3} N n^2 r_k^3 \quad (7)$$

The first term arises by substituting constants  $\alpha = 1$  - provides a single dimension of values,  $T_0$  - melting point,  $\Delta T = T_0 - T_1$  - hypothermia. From (7) we see that the first two terms on the left are negligible compared to the rest. This immediately removes the dependence of  $r_k$  on  $Z$ , i.e, the type of atoms crystallizing substance. Finally, from (7) we have:

$$N \cdot r_k^3 = \frac{1}{\pi n} \cdot \frac{T_0}{\Delta T} \quad (8)$$

If you make an estimate of the average values:  $r_k \sim 1$  nm,  $T_0$  about 1000 (for me-metals),  $\Delta T \sim 100$ ,  $n = N_L$  - number Loschmidt  $\sim 3 \cdot 10^{19} \text{ cm}^{-3}$ , we obtain for the number of particles in the bud  $N \sim 100$ . Below we provide data taken from [11]. We see that our estimates of the formula (8) in qualitative agreement with the experimental data. Indeed, the radius of the embryo practical ski does not depend on the type of metal atoms, the average number of particles  $N$  in the embryo has the same order.

**Table 4.** The parameters of nucleation kinetics at crystallization of supercooled metal [11].

Metal	$T_0$ (K)	$\Delta T$ (K)	$r_k$ (nm)	$N$
Hg	234	90	0,8	100
Sn	505	180	0,8	130
Bi	544	200	0,8	30
Pb	600	170	1,1	180
Ge	1210	295	0,9	130
Ag	1234	253	1,2	430

From (8) it follows that the right side are the parameters, the magnitude of which has not changed over a wide range, i.e.:

$$N \cdot r_k^3 \approx \text{const} \quad (9)$$

Relation (9) is approximately true for many substances. The deep causes of these correlations are not yet clear.

## 5. Conclusion

From the above analysis it follows that the crystal growth in the electric field does not always lead to positive results. Thermodynamic characteristics are to be considered, and it is primarily the magnitude of the Gibbs energy.

## Acknowledgements

This work was financially supported by The Ministry of Education and Science of the Russian Federation in part of the science activity program.

## References

- [1] Yurov V M, Guchenko S A et al. 2012 *Scientific Review* **5** 205–209
- [2] Dhanasekaran R, Ramasamy P 1986 *Nuovo Cimento D* **7** 506–512
- [3] Hammadi Z, Veesler S 2009 *Progress in Biophysics and Molecular Biology* **101** 38–44
- [4] Mullin J 2001 *Crystallization*. Butterworth-Heinemann 600
- [5] Sunagawa I 2005 *Crystals: Growth, Morphology and Perfection*. Cambridge University Press 295
- [6] Duffar Th (Ed.) 2010 *Crystal Growth Processes Based on Capillarity: Czochralski, Floating Zone, Shaping and Crucible Techniques*. Wiley 533
- [7] Shubnikov A V, Porvov V F 1961 *Crystallography* **6** 443–450
- [8] Kozlovsky N M 1962 *Crystallography* **7** 157–159
- [9] Bullakh A G, Bullakh K G 1978 *Physicochemical properties of minerals and components of hydrothermal solutions*. L.: Nedra 167
- [10] Yurov V M, Portnov V S, Ibraev N X and Guchenko C A 2011 *Advances of modern natural science* **11** 55–59